



**WIRE ROPE - 6 x 19 CLASS**



6 x 25 FILLER WIRE WITH FIBER CORE



6 x 25 FILLER WIRE WITH IWRC

According to Federal Specification RR-W-410D, preformed, right regular lay, light lubrication.  
Read important warnings and information preceding wire rope section.

Diameter in Inches	FIBER CORE (IPS)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
3/8	.236	5.49
7/16	.32	7.44
1/2	.42	9.63
5/8	.66	15.0
3/4	.95	21.4
7/8	1.29	29.0
1	1.68	37.6
1.1/8	2.13	47.3
1.1/4	2.63	58.1
1.3/8	3.18	69.9
1.1/2	3.78	82.8
1.3/4	5.15	112.0
2	6.72	144.0
2.1/4	8.51	180.0


Diameter in Inches	IWRC (EIPS**)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
3/8	.26	5.9
7/16	.35	8.0
1/2	.46	10.3
9/16	.59	13.0
5/8	.72	16.1
3/4	1.04	23.0
7/8	1.42	31.1
1	1.85	40.4
1.1/8	2.34	50.9
1.1/4	2.89	62.5
1.3/8	3.50	75.1
1.1/2	4.16	89.0
1.5/8	4.88	103.5
1.3/4	5.67	119.9
2	7.39	154.8
2.1/4	9.36	193.5

Diameter	6 x 24 F.C. (IPS)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
12.5 mm	.35	8.4
16 mm	.54	13.0
19 mm	.81	18.6
22 mm	1.12	25.2
25 mm	1.40	32.8


\*Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.

\*\*CHECK ON AVAILABILITY OF DRAWN GALVANIZED- EIPS

**WIRE ROPE - 6 x 37 CLASS**



6 x 36 WARRINGTON  
SEALE WITH FIBER CORE



6 x 36 WARRINGTON  
SEALE WITH IWRC

According to Federal-Specification RR-W-4100, preformed, right regular lay, medium lubrication.  
Read important warnings and information preceding wire rope section.

Diameter in Inches	FIBER CORE (IPS)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
5/16	.164	3.83
3/8	.236	5.49
1/2	.42	9.63
5/8	.66	15.0
3/4	.95	21.4
7/8	1.29	29.0
1	1.68	37.6
1.1/8	2.13	47.3
1.1/4	2.63	58.1
1.3/8	3.18	69.9
1.1/2	3.78	82.8
1.3/4	5.15	112.0
2	6.72	144.0
2.1/4	8.51	180.0

Diameter in Inches	IWRC (EIPS**)	
	Approx. Weight per foot in Pounds	Breaking Strength in Tons*
5/16	.18	4.12
3/8	.26	5.9
7/16	.35	8.0
1/2	.46	10.3
9/16	.59	13.0
5/8	.72	16.1
3/4	1.04	23.0
7/8	1.42	31.1
1	1.85	40.4
1.1/8	2.34	50.9
1.1/4	2.89	62.5
1.3/8	3.50	75.1
1.1/2	4.16	89.0
1.3/4	5.67	119.9
2	7.39	154.8
2.1/4	9.36	193.5
2.1/2	11.60	236.0
2.3/4	14.00	283.0
3	16.60	333.0

\*Listed for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of catalog Breaking Strength.

\*\*CHECK ON AVAILABILITY OF DRAWN GALVANIZED- EIPS.